



SEM-LIGHT EXTÉRIEUR

EXTERIOR LIGHTWEIGHT FILLER

- + EASY TO USE
- + LIGHTWEIGHT
- + QUICK DRYING
- + FILLS ALL THICKNESSES

TECHNICAL DEFINITION.

Lightweight paste for all repair work on external walls. Non-shrink and fast drying, it is very easy to use for high-quality filling tasks.

COMPOSITION AND APPEARANCE.

Emulsion resin, lightening agent, calcium carbonate and various additives.

The resulting paste is off-white in colour.

ACCEPTED SUBSTRATES.

Exterior walls:

- Painted façades.
- Masonry.
- Rendering.
- Brick.
- Stone.
- Aerated concrete.
- Concrete.
- Cement coating.
- Wood*

*Application on wood : up to 10 mm thick, drying time: 24 hours.

COVERING.

Once the filler is completely dry, it can be covered with all types of coating and paint.

DOCUMENTS TO CONSULT.

NFT 30-608 and EN 16566: Painting fillers for internal and/or external work.

DTU 59.1: Building painting work.

TECHNICAL CHARACTERISTICS.

Second application: 2 to 12 hours.

Drying time before painting: 2 to 48 hours (after complete drying and depending on the weather conditions)

Paste density: 0.8 kg/l.

Adhesion: >0.8 MPa in compliance with EN 16566.

PRECAUTIONS FOR USE.

The temperature on application and during drying must be between +5°C and +35°C.

Do not apply at a humidity level above 80%.

Do not apply to damp substrates.

Not suitable for use on plastic or metal.

Do not inhale dust if sanding.

SAFETY.

A safety data sheet is available at www.quickfds.com. It should be read before use.

Keep out of reach of children.

If swallowed, seek medical advice immediately and show the doctor the packaging or label.

EUH 208 Contains a mixture of: 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1)(55965-84-9).

May trigger an allergic reaction.

PREPARATION OF SUBSTRATES.

Substrates must comply with DTUs, i.e. be clean, dry, hard, cohesive, sound, dust-free and free of any trace of formwork oil.

Correctly open up cracks.

APPLICATION THICKNESS.

All thicknesses.

CONSUMPTION.

Approximately 0.8 kg/m²/mm of thickness.

TYPE OF APPLICATION.

Apply with a filler knife or spatula.

Clean tools with a dry cloth or with water if necessary.

DRYING TIME.

Depends on the substrate, weather conditions and application thickness.

Painting is possible 2 hours after application if filling microcracks and using water-based paint (wait 24 hours for acrylic paint).

PACKAGING.

1 litre and 5 litre buckets.

STORAGE.

12 months in original, unopened packaging, protected from frost and high temperatures.



AFNOR NFT 36.005 classification: Family IV, class 4b

SEMIN

1a, rue de la Gare - F-57920 KEDANGE-SUR-CANNER

Tél. +33 (0)3.82.83.53.57 - Fax: +33 (0)3.82.83.93.33

www.semin.com



MADE IN FRANCE

