



# CE 78 PERFECT'LISS

## LIGHTWEIGHT FINISHING COMPOUND FOR INTERIOR SURFACES

- + HIGH-BUILD POWER
- + HIGH DEGREE OF WHITENESS,  
VERY GOOD COVERING POWER
- + SLIDES VERY WELL
- + EASY SANDING

### TECHNICAL DEFINITION.

CE 78 PERFECT'LISS is a ready-mix lightweight paste compound specially formulated for finishing interior surfaces (walls and ceilings).

### COMPOSITION AND ASPECT.

Resin, water, calcium carbonate, lightweight fillers, preservation agent and various adjuvants.

The paste is white.

### SUITABLE SUBSTRATES.

- Plaster board.
- Plaster block.
- Plaster.
- Concrete.
- Aerated concrete.
- Cement coating.
- Brick.
- Old paintwork.
- Fibreglass.

### COVERINGS.

- Wall covering.
- Paint.

### REFERENCE DOCUMENTS.

- DTU 59.1
- NF 30.608
- DoP.

### PACKAGINGS.

17 kg buckets on covered pallet.

### STORAGE.

18 months in original unopened packaging away from frost and high temperatures.

### PRECAUTIONS FOR USE.

The temperature on application and during drying must be between 8 and 35° C. Do not apply on a wet substrate. Do not use on a frozen substrate.

### PREPARATION OF SUBSTRATES.

The substrates must comply with the DTU 59.1 standard i.e. be dry, clean, hard, free of any trace of separating agent, etc.

### APPLICATION.

Airless application, nozzles 35 and 41 recommended.

### CONSUMPTION.

Variable depending on the thickness applied: 0.4 to 2 kg/m<sup>2</sup>.

### DRYING TIME.

A repeat coat can be made 6 to 24 hours after application of the first coat, depending on the ambient conditions.

### TECHNICAL SPECIFICATIONS.

- Thickness of application: 5 mm maximum.
- Density: 1.3 (1.8 for a traditional filler).
- Reaction to fire: A2s1dO.



USAGE



MECHANICAL  
APPLICATION

# SEMIN

1a, rue de la Gare - F-57920 KEDANGE-SUR-CANNER  
Tél. +33 (0)3.82.83.53.57 - Fax : +33 (0)3.82.83.93.33

[www.semin.com](http://www.semin.com)



MADE IN FRANCE

