



SEMIN TOP G&F

INTERIOR FILLING AND FINISH

- + DIRECTLY APPLY A PAINT FINISH
- + SPECIFICALLY ADAPTED TO FLAT JET ROTOR-STATOR MACHINES
- + IMPROVED WORKING TIME
- + EASY TO SMOOTH

TECHNICAL DEFINITION.

SEMIN TOP G&F is a versatile interior filler plaster suitable for all types of application:

- Airless.
- Spray guns.
- Manual.
- Roller.

Its improved working time allows for a wet-on-wet application and efficient smoothing.

White, smooth, thin. Odourless.

COMPOSITION AND APPEARANCE.

Acrylic emulsion, mineral extender, cellulose derivatives, preserving agent and various adjuvants. The paste is white and has a consistency suitable for all types of application.

SUITABLE SURFACES.

- Plaster board.
- Silicate rock.
- Shuttered concrete.
- Old fibreglass cloth.
- Plaster blocks.
- Floor slabs.
- Aerated concrete.

COVERINGS.

SEMIN TOP G&F can be covered with acrylic or glycol paint.

REFERENCE DOCUMENTS.

- DTU 59.1.
- EN 16-566.

TECHNICAL PROPERTIES.

- Dry extract: 71%.
- Density: 1.7.
- VOC: <1g/l.

PACKAGINGS.

25 kg plastic bags and 20 & 25 kg pails on a covered pallet.

STORAGE.

18 months in a frost-free place in original unopened packaging.

PRECAUTIONS FOR USE.

- Do not apply in temperatures < +8°C and > +35°C and relative humidity > 70%.
- Do not apply to overheated surfaces.
- Do not apply to damp surfaces.
- It is recommended to wear goggles when spraying as protection against small particles.

PREPARATION OF SURFACES.

The surfaces must comply with the DTU 59.1 standard i.e. be dry, clean, hard, free of any trace of separating agent, etc.

APPLICATION.

SEMIN TOP G & F can be applied with any type of spray machine adapted to thick materials, sprayed with an airless pump (capacity >5 litres/min, nozzles 531 to 535), and applied manually with a plaster knife or roller.

Easy smoothing in 1 or 2 coats depending on the condition of the substrate and the desired finish.

DRYING TIME.

5 to 12 hours depending on the amount applied and according to the temperature, relative humidity and aeration of the room.

CONSUMPTION.

Variable depending on the thickness applied: 1 kg to 2.5 kg/m² and per coat.

AFNOR NFT 36-005 - Family III - Class 2



USAGE



MANUAL APPLICATION



MANUAL APPLICATION



MECHANICAL APPLICATION

SEMIN

1a, rue de la Gare - F-57920 KEDANGE-SUR-CANNER
Tél. +33 (0)3.82.83.53.57 - Fax : +33 (0)3.82.83.93.33

www.semin.com



VOC content <1 g/L



MADE IN FRANCE

